

PVDF-FOAM ZOTEK® F

OSU Flexible

Applications laminates	Interior soft trim in combination with leathers, textiles and decorative
Material it	closed cell Polyvinylidenfluorid (KYNAR®)-Foam. Unique properties make ideal for a wide range of applications.
Colour	white
Typical properties	Flexible, formable, flame propagation resistant, low heat release (OSU), UV-resistant, low water absorption
Density	approx. 33 kg/m ³
Thickness	25 mm
Dimensions	2000 mm x 1000 mm
Flammability	meets the requirements of ABD 0031, CS/FAR 25.856(a) CS/FAR 25, App F, Part I (a)(1)(ii) CS/FAR 25. App. F Pt IV CS/FAR 25. App. F Pt V
Temperature range	- 55 °C to + 110 °C
Characteristics	- good mechanical performance - fine uniform and closed-cell structure - very low water absorption - low water vapour transmission rate - odourless - non-toxic - non-staining
Processing	PVDF-Foam can be ... - cut - punched - skived - thermo laminated - welded - thermo formed - bonded - press formed ... without problems!

PVDF-FOAM ZOTEK® F

OSU Flexible



Properties	Standard	Unit	F OSU Flexible ¹⁾
Density	ISO 845	kg/m ³	33
Compression stress-strain characterist.	25% compression	ISO 7214	kPa max. 60 1st compression
Tensile strength	ISO 1798	kPa	min. 245
Elongation at break	ISO 1798	%	min. 88
Compressions set	ISO 7214/ASTM 22 h @ 50 % compression, 23 °C	% set	max. 17 D35751, 25mm c/c
Water absorption	ASTM 1056	%	2.2
Storage time		-	unlimited
Thermal conductivity at 40 °C	ISO 8301	$\frac{W}{m \cdot K}$	0.038
Heat release mm 25mm	CS/FAR 25.853(d) App F Pt IV	2 min. total HR (kWmin/m ²): 39.9 at 25 CS/FAR 25 App F Pt IV Peak HR (kW/m ²): 49.1 at	
Smoke density	CS/FAR 25.853(d) CS/FAR 25 App F Pt V	pass at 13 mm	
Smoke density	ABD0031 para.2.3.2	pass at 13 mm	
Toxic gas emission	ABD0031 para.2.3.2	pass at 13 mm	
Vertical bunsen burner	CS/FAR 25.853(a) CS/FAR 25 App F Pt I(a)(1)(ii)	pass at 25 mm	
Radiant heat panel	CS/FAR 25.856(a) CS/FAR 25 App F Pt VI	pass at 3 mm and 25 mm	

1) Typical Value

PVDF-FOAM ZOTEK® F

OSU Flexible / 63

self adhesive



Properties	Standard	Unit	F OSU Flexible ¹⁾
Density ²⁾	ISO 845	kg/m ³	33 (foam without adhesive)
Compression stress-strain characterist 25% compression ²⁾	ISO 7214 1st compression	kPa	max. 60
Tensile strength ²⁾	ISO 1798	kPa	min. 245
Elongation at break ²⁾	ISO 1798	%	min. 88
Compressions set ²⁾ 22 h @ 50 % compression, 23 °C ½ hr recovery	ISO 7214/ASTM D35751, 25mm c/c	% set	max. 17
Water absorption ²⁾	ASTM 1056	%	2.2
Storage life at 10-25°C, 10-70% RH			12 months
Temperature range	- 55 °C to + max. 85 °C		
Thermal conductivity at 40 °C ²⁾	ISO 8301	$\frac{W}{m \cdot K}$	0.038
Flammability:	Test: AITM 2.0002B, one side bonded on 0,5 mm Aluminium sheet Requirement: CS/FAR-25, App.F, Part I, (a)(1)(ii)		
1) Typical Value			
2) without adhesive			